Adhesive Systems, Inc.

TECHNICAL DATA SHEET
TDS #: RP 750
CYANOACRYLATE ADHESIVE

REVISED: DECEMBER/2010

ADVANCE PERFORMANCE SERIES
RP 750 CYANOACRYLATE ADHESIVE

GENERAL PURPOSE BONDING

DESCRIPTION:

RP 750 is a medium viscosity, rapid curing, cyanoacrylate adhesive. It is designed to bond a wide range of similar and dissimilar materials. Handling strength in most applications is in 10 seconds.

PHYSICAL PROPERTIES:

Color:	**Clear**
Viscosity:	**750 cps**
Specific Gravity:	**1.05**
Base:	**Ethyl**

PERFORMANCE PROPERTIES:

Substrate	*Fixture Time*	*Bond Strength*
Steel	< 20 Seconds	> 2100 psi
Aluminum	< 15 Seconds	> 1750 psi
Neoprene	< 5 Seconds	> 750 psi
ABS	< 10 Seconds	> 900 psi
PVC	< 5 Seconds	> 900 psi
Polycarbonate	< 30 Seconds	> 900 psi
Phenolic	< 10 Seconds	> 850 psi

NOTE: Method used, ISO 4587.

Tensile Strength:

Steel: > 1800 psi

NOTE: Method used, ISO 6922

ELECTRICAL PROPERTIES:

Dielectric Constant	ASTM D 150 Dissipation Factor
1 kHz	2 to 3.50/ < 0.02

Volume Resistivity ASTM D 257: 2 x 10^{15} to 10 x 10^{15}

FACTORS AFFECTING CURE SPEED:

GAP: Thin bond line results in faster cure speed. Larger gaps will lengthen cure speed.
HUMIDITY: Cure and fixture times can be influenced by the humidity conditions at the time of assembly. The higher the RH the faster cure and fixture times will be. Fixture time data based on our testing is conducted at 50% relative humidity.

What we bond:

ABS	*NBR*
Acrylic	*Neoprene*
Aluminum	*Nitrile*
Bakelite	*Nylon*
Brass	*Phenolic*
Chloroprene	*Polycarbonate*
Chrome	*Polyester*
Cooper	*Polystyrene*
EPDM	*Porcelain*
Fiberglass	*PVC*
Latex	*SBR*
Leather	*Steel*
Natural Rubber	*Valox*
	Wood

CHEMICAL/SOLVENT RESISTANCE:

% OF STRENGTH RETAINED AFTER AGING FOR 500 HOURS

GASOLINE @ 22^{0}C:	*100%*
ISOPROPANOL @ 22^{0}C:	*100%*
ETHANOL @ 22^{0}C:	*100%*
FREON TA @ 22^{0}C%	*100%*
MOTOR OIL @ 40^{0}C%	*100%*
POLYCARBONATE 40^{0}C @ 95% RH	*100%*

DIRECTIONS FOR USE:

For optimum results parts should be clean and free from any contamination on the bonding surface. If parts do not mate flush together use a higher viscosity product to compensate for the gap. Any excess adhesive can be removed using Remove Debonder.

STORAGE:

Store product in unopened containers, out of direct sunlight, in a dry location. Material should be stored at or below 22^{0}C. For extended shelf life unopened containers of the product may be refrigerated.

NON WARRANTY: Information contained herein is based on test and information we believe to be reliable and accurate. It is offered in good faith for the benefit of the consumer. ASI shall not be liable for any injury, loss, or damage, in the use of it's chemical products since the conditions of us are beyond our control. In every case we urge and recommend the user conduct tests to determine to their own satisfaction that the product is of acceptable quality and suitable for their particular purpose under their own operating conditions. Statements concerning the possible use of our products are not intended as recommendations or to use our products in the infringement of any patent. These products are for Industrial Use only.

Engineering Excellence
For technical information
and support call **1-800-552-0299** or visit our website at
www.instantca.com

www.comoso.com